



OKS 1765

Sliding Film for thread-forming Screws, water-based concentrate



Description

OKS 1765 is a sliding film for thread-forming screws.

Applications

- Coating of threads of aluminum alloys, high-alloyed, galvanized and austenitic steels to reach controlled friction values during assembly and facilitate thread forming
- Prevents cold-fretting

Branches

- Paper and packaging industry
- Rubber and plastic processing
- Municipal services
- Shipbuilding and marine technology
- Iron and steel industry
- Rail vehicle technology
- Plant and machine (tool) engineering
- Chemical industry
- Logistics
- Glass and foundry industry

Application tips

For best results clean the surface, first mechanically and then with OKS 2610/ OKS 2611 Universal Cleaner. The surfaces to be coated have to be metallic blank and dry. The dilution with water up to 1:5 depends on the desired friction value. Stir well before use. The best application can be reached through dipping or spraying, sometimes through brushing an evenly thin film on the prepared surface. Observe the drying times according to the following technical data. Protect the containers from frost.

Packaging

- 5 l Canister
- 25 l Canister

Advantages and benefits

- Economical through low consumption (can be diluted with tap water)
- Does not contain any toxic components and is therefore sanitary harmless
- The water-soluble ingredients are biodegradable, the water-nonsoluble ingredients are ecologically neutral
- Forms a colourless, adhesive and tackfree sliding film after drying
- Includes an inhibitor, which prevents corrosion during the drying
- The coating can be checked easily through a fluorescent ingredient



OKS 1765

Sliding Film for thread-forming Screws, water-based concentrate

Technical Data

	Standard	Conditions	Unit	Value
Main components				
solvent				isopropanol
solvent				water
solid lubricants				synthetic wax
additives				corrosion protection
Application related technical data				
flashing point	DIN EN 22 719		°C	42
melting temperature of the waxes			°C	125
upper operating temperature			°C	70
processing temperature			°C	20-25
drying time		20°C	min	30
curing temperature			°C	max. 60
colour				milky-white
density (at 20°C)	DIN EN ISO 3838		g/cm ³	1
thread friction coefficient (μ total)	DIN EN ISO 16 047	screw ISO 4017 M10x55-8.8 black-oxide, nut ISO 4032 M10-10 black-oxide		0.06-0.15
Product specific technical data				
dilution				with water, up to 1:5
pH value				approx. 8.5 (concentrate)
thread tapping torque	EN ISO 7085	screw M10	Nm	< 20

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47
 82216 Maisach
 Phone: +49 (0) 8142 3051 - 500
 info@oks-germany.com
 www.oks-germany.com



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark
Safety data sheet for industrial and commercial users is available for downloading under www.oks-germany.com. Our Customer and Technical service will be pleased to help should you have any further questions.