


OKS 252

White High-Temperature Paste for Food Processing Technology



Description

OKS 252 is a metal-free high temperature paste for lubrication of screws, bolts and sliding surfaces that are subjected to high pressures, high temperatures at low speeds or oscillating movements.

Applications

- Lubrication of all kind of high stressed sliding areas, especially at low sliding speeds or oscillating movements, e.g. at threads, joints and bayonet nut connectors made of steel or non ferrous metals
- Assembling paste with corrosion protection for screws, bolts, spikes, bushings, flanges, spindles and fittings in the whole food stuff industry
- Separation of high temperature stressed screw joints, even after a long operation time

Branches

- Shipbuilding and marine technology
- Logistics
- Paper and packaging industry
- Catering equipment and food processing technology
- Glass and foundry industry
- Rubber and plastic processing
- Plant and machine (tool) engineering
- Chemical industry
- Municipal services
- Rail vehicle technology
- Iron and steel industry

Advantages and benefits

- Adheres good on metal surfaces, has a good water resistance and corrosion protection
- Good water resistance
- Prevents from tribo-corrosion
- Contains no metal pigments and is free of sulphurous materials
- Neutral to alloyed steels
- Formulation according to the FDA guideline 21CFR 178.3570
- Registered by the NSF H1
- MOSH/MOAH-free



PRODUCT INFORMATION

OKS 252

White High-Temperature Paste for Food Processing Technology

Application tips

For optimal adhesion clean thread and sliding areas from dirt and other lubricants, first mechanically (e.g. with wire brush) and then with OKS 2610/OKS 2611 Universal Cleaner. Apply paste evenly in a sufficient amount onto head and nut support and thread or onto the sliding areas with brush, spatula, etc. Paste has also sealing properties. Do not use paste instead of grease and mix with suitable lubricants only.

Packaging

- 200 g Dispenser
- 250 g Brush tin
- 1 kg Can

Technical Data

	Standard	Conditions	Unit	Value
Main components				
base oil				polyglycol
thickener				silicate
solid lubricants				white solid lubricants
Application related technical data				
viscosity at (40°C)	DIN 51 562-1		mm ² /s	360
viscosity at (100°C)	DIN 51 562-1		mm ² /s	57
flashing point	DIN ISO 2592	> 79	°C	> 200
worked penetration	DIN ISO 2137	60DH	0.1 mm	265-295
lower operating temperature			°C	-30
upper operating temperature		lubrication	°C	160
upper operating temperature		separation	°C	1,200
colour				light grey
density (at 20°C)	DIN EN ISO 3838		g/cm ³	1.6
water resistance	DIN 51 807-1	90°C	Degree	1-90
thread friction coefficient (μ total)	DIN EN ISO 16 047	Screw ISO 4017 A2 M10x55-70, Nut ISO 4032 A2 M10-70		0.12
breakaway torque	DIN 267-27	M10 A2, 40 Nm, 400°C, 100h	Nm	< 3.2 x tightening torque
press-fit test	draft DIN 51 833		μ	0.12
Properties and approvals				
approval for food processing technology				NSF H1, Reg.-Nr. 135748

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47
 82216 Maisach
 Phone: +49 (0) 8142 3051 - 500
 info@oks-germany.com
 www.oks-germany.com



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark
Safety data sheet for industrial and commercial users is available for downloading under www.oks-germany.com. Our Customer and Technical service will be pleased to help should you have any further questions.